

Formula Digital

SD-Papier mit ausgezeichnete Qualität bis zur letzten Durchschrift dank innovativer Non-Contact Technologie

Technische Daten

Formula Digital CB	weiß		
Flächengewicht	ISO 536	g/qm	80 ±4
Dicke	ISO 534	μm	102 ± 4
Opazität	ISO 2471	%	87 ±4
Relative Feuchte	TAPPI T502 om-89	%	40 ±5

Formula Digital CFB	weiß /gelb /grün / blau / rosa		
Flächengewicht	ISO 536	g/qm	80 ±4
Dicke	ISO 534	μm	101 ± 4
Opazität	ISO 2471	%	88 ±4
Relative Feuchte	TAPPI T502 om-89	%	43 ±5

Formula Digital CF	weiß / gelb / grün / blau / rosa		
Flächengewicht	ISO 536	g/qm	80 ±4
Dicke	ISO 534	μm	100
 Opazität	ISO 2471	%	88 ±4
Relative Feuchte	TAPPI T502 om-89	%	40 ±5

Anwendungen:

Formulare, Quittungen, Überweisungen, Abholscheine, Lieferscheine, Vordrucke

Umweltrelevante Produktzertifikate und Informationen

• FSC®-zertifiziert (FSC® COO3945)

Technische Produktzertifikate und Informationen

Empfohlen für Laser/Trockentoner

Hersteller-Zertifikate

- Qualitätsmnagementsystem (ISO 9001)
- Umweltmanagementsystem (ISO 14001)
- Arbeits-und Gesundheitsschutzmanagementsystem (ISO 45001)
- Energiemanagement (ISO 50001)w







Manufactured in a mill with quality management



Manufactured in a mill with environmental management



Manufactured in a mill with health and safety management



Manufactured in a mill with energy management



Empfohlen für Laser / Trockentoner

OVOL Papier Deutschland GmbH Osterbekstraße 90a 22083 Hamburg Deutschland www.ovol.de